RU10-6-6.3 OZ PE 6.3 OZ POULTRY HOUSE FABRIC

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

DESCRIPTION

A premium coated fabric with enhanced UV protection for use in garage, specialized covers, and other applications demanding superior performance.

FABRIC SPECIFICATIONS

Weave:	Woven clear UV stabilized HDPE
	tapes
Coating:	1.75 mil average each side
	(41 g/m²/side)
Color:	Clear or other colors available
	upon request
Weight:	6.3 oz/yd² (215 g/m²)

ROLL SPECIFICATIONS

Cores: 4 inch (101.6 mm) or 5 inch (127 mm) I.D. available Width: Up to 144 inches (-0, +0.5) as ordered, 3.66 (-0, +12 mm) Length: Minimum 500 yds/roll (457 m); up to 1000 yds/roll (914 m)

These values are typical data and are not intended as limiting specifications.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.565.2000

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 05/14

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. These data should not be considered specification.

Grab Tensile Warp 220 lb 979 N / Weft 220 ll	b 979 N
ASTM D5034	
Tongue Tear Warp 70 lb, 311 N / Weft 75 lb, ASTM D2261	333 N
Mullen Burst415 psi / 2859 kPaASTM D3786	
Accelerated UV>80 % strength retention after 2Weathering1exposure @ 0.77 W/m²/nm, orASTM G154exposure @ 1.35 W/m²/nm.	
¹ Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50 ² 1333 MJ)°C
х — — — — — — — — — — — — — — — — — — —	

