RB88X-6 350 MEMBRANE STRUCTURE FABRIC

DESCRIPTION

NovaShield[®] brand RB88X-6 350 is a heavyweight fabric that incorporates a special weave pattern to enhance thickness, flatness and tear properties. The weave also improves hydrostatic resistance. RB88X-6 350 is excellent for applications requiring low light transmittance and UV stability, such as membranes structure end covers and agriculture barns.

FABRIC SPECIFICATIONS

Weave:	Woven black HDPE scrim
Coating:	2.5 mil average each side (59 g/m²/side)
Color:	Black or colored coatings available
Weight:	10.5 oz/yd² (356g/m²) +/- 10%
Thickness	: 20 mil (0.51mm) +/- 10%, ASTM D1777

ROLL SPECIFICATIONS

Cores:	4 inch I.D. or 5 inch I.D. available
Width:	Up to 144 inches (-0, +0.5) as
	ordered
Length:	Minimum 500 yds/roll;
-	up to 2000 yds/roll

These values are typical data and are not intended as limiting specifications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.565.2000

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 4/15

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Warp 240 lb/in (2131)/Weft 270 lb/in (2398)
Warp 140 lb 622 N / Weft 160 lb 710 N
Warp 140 lb 622 N / Weft 140 lb 622 N
720 psi / 4960 kPa
>90% strength retention after 2000 hrs exposure @ 0.77 W/m²/nm, or 1200 hrs exposure @ 1.35 W/m²/nm

