

# G483W, G483B

## DOUBLE-COATED WINDOW GLAZING FOAM TAPE

### DESCRIPTION

Cross-linked high density polyethylene, closed cell foam coated on both sides (double-coated) with a permanent bonding acrylic pressure-sensitive adhesive protected by an easy release treated 4 mil PE film liner (light blue). Flexible foam material is effective for sealing, highly resistant to water, chemicals, UV light and varied temperature. Adhesion allows permanent bond to a variety of irregular surfaces.

### PRODUCT APPLICATION

AAMA Certified for glazing applications.

Can also be used for mounting and joining nameplates, signs, plaques, point-of-purchase, plastic hooks, mirror trims, etc. General-purpose indoor / outdoor mounting and joining.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
Customer Service: 800.IPG.8273 | 800.474.8273  
Tape Technical Service: 877.447.4832  
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 05/16

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

<b>Backing</b>	Closed cell / Cross-linked PE foam
<b>Colors</b>	White, Black
<b>Adhesive</b>	Solvent Acrylic
<b>Adhesion to Steel</b> (oz/in of width) PSTC-3	52.9 (1.5 kg/25mm)
<b>Density</b> (PCF)	2.5
<b>Total Thickness w/o Liner</b> (inch) PSTC-133	1/8" (3.0mm)
<b>Shear Adhesion</b> (hours) (1" x 1" x 1 kg @ 77°F (25°C) PSTC-107	>10
<b>Service Temperature</b> (Long term)	-22°F to +176°F (-30°C to +80°C)

