4616 **GLASS CLOTH** ELECTRICAL TAPE

DESCRIPTION

Woven fiberglass backing imparts high temperature resistance and thermal stability and offers outstanding abrasion resistance for a large number of applications. Offers high adhesion and resistance to tearing. Rubber thermosetting adhesive system give the tape excellent solvent resistance.

PRODUCT APPLICATIONS

Coil insulation wrap, relay coverings, protective insulating wrap on solenoid coils, splicing on electrical transmission lines. Ideal for motor repair shops for bundling and banding heavy gauge magnet wire.

GOVERNMENT COMPLIANCE

MIL-T-4053B



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 11/13

INTERTAPE POLYMER GROUP® **TECHNICAL DATA SHEET**

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Glass Cloth
Backing Thickness	5.0 mil (0.127 mm)
Adhesive	Rubber Thermosetting
Color	White, Black
Total Thickness	7.0 mil (0.178 mm)
Dielectric Strength	2500 Volts
Temp. Class	155°C / F
Insulation Resistance	10 ³ megohms
Tensile Strength	175 lbs/in (306 N/cm)
Adhesion to Steel	50 oz/in (5.5 N/cm)
Elongation	3%
Electrolytic Corrosion	1.0 Direct/ A, 1*
Flammability	BU 2*
Storage Stability	Very Good
Solvent Resistance	Excellent
Moisture Resistance	Excellent
UL File #	E20780
CSA File #	LR94980
*VDE 0340	



