

99149

MEDIUM TEMP MEDIUM GRADE PAPER MASKING TAPE

DESCRIPTION

99149 is an aqua colored, conformable, saturated, crepe paper masking tape with pressure-sensitive rubber adhesive. Good adhesion and holding properties. Clean, easy removal. Resists paint flaking and wet sanding. Compatible with both water and solvent-based paints. Three (3) day UV resistance. Temperature resistant up to 225°F (107°C) for 30 minutes.

PRODUCT APPLICATION

For paint masking requiring adhesion to and removal from a variety of surfaces.

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to one (1) year from the date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within six (6) months of date of shipment.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 04/25

IPG®

TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Crepe Paper
Adhesive	Natural Rubber / Resin
Tensile Strength (lbs/in. width) ASTM D3759	23 (100 N/25mm)
Elongation (% at break) ASTM D3759	12
Adhesion to Steel (oz./in. width) ASTM D3330	28 (7.6 N/25 mm)
Quick Stick (oz./in. width) PSTC-5	
To kraft	5 (1.4 N/25mm)
To steel	14 (3.8 N/25mm)
Total Thickness (mils) ASTM D-3652	6.6 (0.17 mm)
Color	Aqua (Blue-Green)

